

Product	M0-858-1226-001 EPOSSIPOL LUCIDO GIALLO FLUO
Series: M0 Group: M0004000	EPOXY-POLYESTER THERMOSETTING POWDER COATING FOR INDOOR USE

SPECIFIC PRODUCT PROPERTIES

<u>CURE TEMPERATURE:</u>	180	°C	Object temperature
<u>CURE TIME:</u>	20	Min	-
<u>GLOSS AT 60 °:</u>	80 - 90	% Units %	ISO 2813
<u>THEORIC OUTPUT:</u>	10.34	m ² /Kg	Thickness 60 µm
<u>APPLICATION:</u>	Corona	-	-

Polymerization area (Object temperature)	Temperature (°C)	Min time (min)	Max time (min)
	170	20	35
180	15	27	
200	8	15	

GENERAL PROPERTIES OF THE SERIES

Fundamental product characteristics

Powder coatings of this **Series** are based on high quality raw materials conveniently chosen to optimally balance mechanical and chemical properties of the painting system. However, the fluorescent pigments used in these products, are characterised by **low light fastness**. This could cause an evident colour modification when the finish is exposed to direct or indirect sunlight. To improve the lighth fastness, a clear powder should be applied over the fluorescent finishing.

Substrate preparation

Before the painting, the item should be adequately pre-treated in accordance with surface type, final use and required performances. The following table can be used as starting point for the pre-treatment choice.

Substrate	Indoor Use	Outdoor Use	Architecture
Aluminium	Soil removal, Chromate, Chrome-Free	-	-
SteelAcciaio	Soil removal, Iron Phosphate, Zinc Phosphate, Sand-blasting	-	-
Zinc coated steel*	Acid attack, Iron Phosphate, Zinc Phosphate, Chromate	-	-

* If the powder has to be applied on galvanized steel, please contact the representative.

Particle size distribution

Powder coatings of this **Series** are characterized by an average particle size included between 30 and 40 microns. According to the customer's specific needs, specific particle size distributions can be supplied.

Typical applications

Powder coatings of this **Series** can be used for painting several products for indoor use.

Storage stability

The self-life of this Powder coatings Series, if stored in a dry place and at temperatures below 30°C, will be at least 36 months from production date. For product older than 36 months, it is recommended to check the characteristics before use.

General properties of the series ⁽¹⁾	Regulation	Test result
Impact Test ⁽²⁾	ASTM D2794	2,5 Nm
Adhesion ⁽²⁾	ISO 2409	GT0
Deep-drawing	ISO 1520	5 mm
Bending test ⁽²⁾	ISO 1519	5 mm
Salt spray ⁽³⁾	ISO 9227	500 hours without film separation
Humidity test ⁽³⁾	ISO 6270-2	500 hours without film separation or blistering
Acetone	100 double passages with cotton wad	Scarce resistance
Ethyl alcohol	100 double passages with cotton wad	Excellent resistance
Methylethylketone	100 double passages with cotton wad	Scarce resistance
Perchloroethane	100 double passages with cotton wad	Scarce resistance
Toluene	100 double passages with cotton wad	Limited resistance
Trichloroethane	100 double passages with cotton wad	Scarce resistance
Xylene	100 double passages with cotton wad	Limited resistance
Acetic acid (10%)	Film immersion for 30 days	Excellent resistance
Citric acid (10%)	Film immersion for 30 days	Excellent resistance
Hydrochloric acid (10%)	Film immersion for 30 days	Excellent resistance
Phosphoric acid (10%)	Film immersion for 30 days	Excellent resistance
Lactic acid (10%)	Film immersion for 30 days	Excellent resistance
Sulphuric acid (10%)	Film immersion for 30 days	Excellent resistance
Ammonium hydroxide (10%)	Film immersion for 30 days	Scarce resistance
Sodium hydroxide (10%)	Film immersion for 30 days	Scarce resistance

⁽¹⁾ All tests were performed on smooth glossy white powder without fillers sensitive to acids. For physical-chemical tests on specific codes please contact the Technical Direction of ST Powder Coatings.

⁽²⁾ Tests carried out on Unichim steel panels with coating thickness of about 60 microns.

⁽³⁾ Tests carried out on Bonder 26S/60/0C panels with coating thickness of about 60 microns.

Note 1

The information given in this Technical Data Sheet, based upon laboratory tests, is currently correct to the best of our knowledge. Since product application and conditions vary and are often beyond our control, we can guarantee only the product quality itself. In the light of continuous product improvement, ST Powder Coatings reserves the right to modify without notice the content of this technical sheet.

Note 2

The acronym RFG, if present in the description, indicates a product formulated with special additives that minimize the problems related to direct polymerization in gas ovens.